



Dendritic Architecture for the Delivery of Levofloxacin against Resistant Producing Strains

Madhusudhan Reddy Annapureddy, Srinivas Nelavalli, Karthikeyan Ramadoss and P. Srinivasababu

¹Department of Biotechnology, Acharya Nagarjuna University, Guntur, AP, INDIA

²Department of pharmaceuticals, Vignan Pharmacy College, Vadlamudi, Guntur, AP, INDIA

Available online at: www.isca.in

Received 27th August 2012, revised 13rd August 2012, accepted 17th August 2012

Abstract

The present study was aimed at developing and exploring the use of PEGylated poly (propylene imine) dendritic architecture for the delivery of an anti-bacterial drug, Levofloxacin. For this study, PEGylated poly(propylene imine) dendritic architecture was synthesized and loaded with Levofloxacin and targeted to the resistant producing strains of *Klebsiella pneumoniae* and *E.coli*. The antibacterial activity was carried out by cup and bore method to compare the zone of inhibition with standard drug and control (DMSO). The study showed that the Levofloxacin loaded dendrimer has significant antibacterial activity than the plain drug and control treated, but standard drug was not shown zone of inhibition upon both microorganisms. In this study antibacterial activity of synthesized system are also relatively safer and hold potential to deliver some other drugs also.

Keywords: Dendrimers, PE Glylation, levofloxacin, resistant producing strains.

Introduction

Dendrimer represents a novel type of polymeric material. It is also known as starburst¹ or cascade² or molecular trees³ or arborols, or polymers. They attract the increasing attention of all because of their unique structure, high degree of control over molecular weight and the shape that has led to the synthesis of unimolecular micelles⁴⁻⁷. Considering the use of dendrimers for drug delivery, it is necessary that they are nontoxic and biocompatible. However, it has been demonstrated that widely used dendrimers, such as PAMAM and poly (propylene imine) (PPI) dendrimers bearing primary amino group termini, are quite cytotoxic, and also these dendrimers were cleared rapidly from the circulation when administered intravenously⁸⁻¹¹. Poly ethylene glycol (PEG) is typically a clear, colorless odorless substance that is soluble in water, stable to heat, inert to many chemical agents, that does not hydrolyze or deteriorate, and is generally non-toxic, PEG is considered to be biocompatible, which is to say that PEG is capable of coexistence with living tissue or organisms without causing harm, as reviewed earlier^{12,13}. It has been shown that covalent attachment of poly (ethylene glycol) to proteins decreases their immunogenicity and increases their circulation time^{14,15}. Moreover, a number of studies have demonstrated that poly (ethylene glycol) chains grafted to surface of polymer micelles and liposomes suppress their interaction with plasma proteins and cells and prolong their blood elimination half-life¹⁶⁻²¹. On the basis of these findings, it seems that dendrimers covered with poly (ethylene glycol) grafts are attractive compounds as drug carriers in *in vivo*. Such molecules are expected to encapsulate drugs in their dendrimer moiety and reveal biocompatibility due to their hydrophilic shell

consisting of poly (ethylene glycol) grafts. The present study was aimed at developing and exploring the use of PEGylated newer EDA-PPI dendrimers for delivery of anti-bacterial drug, Levofloxacin. Levofloxacin was selected for incorporation into PEGylated ethylenediamine (EDA)-PPI dendrimers based on its antibacterial activity. PEGylation of EDA-PPI dendrimers establishes suitability of PEGylated dendrimer as a drug delivery system for Levofloxacin.

Material and Methods

Material: PEG2000, Reney Nickel (Sigma, Germany), Raney Nickel (Merck, India), triethylamine, dioxan, ethylenediamine, acrylonitrile (CDH, India), N, N dicyclohexyl carbodiimide (DCC), Cellulose dialysis bag (MWCO 12-14 Kda, Himedia, India), 4 dimethyl amino pyridine (sd-fine chemicals, India), Agar plates (Hi media, Mumbai), Levofloxacin was a benevolent gift from Hetero Pharmaceuticals, Hyderabad, India.

Methods: Synthesis of 5.0G EDA-PPI Dendrimers: EDA-PPI dendrimers were synthesized by the previously reported and established procedure²². The half generation EDA-dendrimer-(CN) 4_n (where *n* is generation of reaction or reaction cycle) was synthesized by double Michael addition reaction between acrylonitrile (2.5 molar times per terminal NH₂ group of core amine moiety) and aqueous solution of ethylenediamine or previous full generation dendrimers. After the initial exothermic phase, the reaction mixture was heated at 80°C for 1 h to complete the addition reaction. The excess of acrylonitrile was then removed by vacuum distillation (16 mbar, bath temperature

40°C). The full generation EDA-dendrimer-(NH₂)_{4n} was obtained by hydrogenation in methanol at 40 atm hydrogen pressures and 70°C for 1 h with Reney Nickel (pretreated with hydroxide and water) as catalyst. The reaction mixture was cooled, filtered and the solvent was evaporated under reduced pressure. The product was then dried under vacuum. EDA-PPI dendrimers up to 5.0G were prepared by repetition of all the above steps consecutively, with increasing quantity of acrylonitrile

Synthesis of PEGylated 5.0G EDA-PPI Dendrimers: To a solution of 5G EDA-PPI dendrimer (0.01 mmol) in dimethyl sulfoxide (DMSO) (10 ml), PEG 2000 (0.32 mmol) in DMSO (10 ml) and N, N dicyclohexyl carbodiimide (DCC) (0.32 mmol) in DMSO (10 ml) were added and the solution was stirred for 5 days at room temperature. The product was precipitated by addition of water, filtered and dialyzed (MWCO 12-14 Kda, Himedia, India) against double distilled water for 24 h to remove free PEG 2000, DCC and partially PEGylated dendrimers followed by lyophilization (Heto drywinner, Germany).

Drug Loading in Formulation: The known molar concentrations of EDA-PPI dendrimer and PEGylated 5.0G dendrimers were dissolved separately in methanol and mixed with methanolic solution of Levofloxacin (100 mol). The mixed solutions were incubated with slow magnetic stirring (50 rpm) using teflon beads for 24 h. These solutions were twice dialyzed in cellulose dialysis bag (MWCO 1000 Da Sigma, Germany) against double distilled water under sink conditions for 10 min to remove free drug from the formulations, which was then estimated spectrophotometrically (λ_{max} 288 nm) (UV-1601, Shimadzu, Japan) to determine indirectly the amount of drug loaded within the system. The dialyzed formulations were lyophilized and used for further characterization.

Antibacterial assay (Agar well diffusion method): About two human pathogenic bacterial strains were used. *Klebsiella pneumoniae* and *E.coli* were tested against the Levofloxacin loaded dendrimer. The antimicrobial activity of Levofloxacin loaded dendrimer was determined by agar well diffusion method against different bacteria as described. In this method, pure isolate of each bacterium was sub-cultured in nutrient broth at 37°C for 24h. One hundred microlitres (about 106CFU/mL, standardized by 0.5 Mac-Farland) of each test bacterium was spread with the help of sterile spreader on to a sterile Muller-Hinton Agar plate so as to achieve a confluent growth. The plates were allowed to dry and a sterile cork borer of diameter 6.0mm was used to bore wells in the agar plates. Subsequently, a 50µL volume of the dendrimer, pure Levofloxacin and drug loaded dendrimer was introduced in triplicate wells into Muller-Hinton Agar plate. The plates were allowed to stand for 1h or more for diffusion to take place and then incubated at 37°C for 24h. The zone of inhibition was recorded to the nearest size in mm.

Results and Discussion

The polypropyleneimine dendrimer was synthesized by using ethylenediamine as a core. The synthesized dendrimer were further PEGylated with PEG 4000. The PEGylated dendrimer is used as carrier system in which Levofloxacin was loaded and drug entrapment efficiency was calculated as 60.2±0.03. The antibacterial activity of drug loaded dendrimer was performed by agar well diffusion method. The results are compared with plain dendrimer and pure Levofloxacin and thus, it reveals that the PEGylated drug loaded dendrimer shows potent activity than that of plain drug on both the selected organisms (table-1 and figure-1 to 6). Further, it was observed that the Levofloxacin does not show inhibitory zone. Hence it clarifies that the selected organisms are resistant to Levofloxacin. Thus, the synthesized PEGylated polypropyleneimine dendrimer is an effective carrier to target any antibacterial agent for resistant producing organism.

Conclusion

From the present study it can be concluded that the prepared Levofloxacin loaded PPI dendrimer were highly effective against both the resistant producing organisms. However the synthesized system was found to be suitable and safe to deliver any drug to the targeting sites.

Acknowledgement: The authors are thankful to P.Sowjanya for providing facility to do antibacterial activity of synthesized system.

References

1. Tomalia D.A., Naylor A.M. and Goddar W.A., Poly (Amidoamine) Dendrimer-Templated Nanocomposites, 1. Synthesis of Zerovalent Copper Nanoclusters *Angew, Chem.*, **102**, 119 (1990)
2. Tomalia D.A., Durst H.D., Dendrimers II: Architecture, Nanostructure and Supramolecular Chemistry, *Top. Curr. Chem.*, **165**, 193 (1993)
3. Fréchet J.M.J., Inorganic and Organometallic Macromolecules: Design and Applications, *Science*, **263**, 1710 (1994)
4. Voit B.I., Dendritic polymers: from aesthetic macromolecules to commercially interesting materials, *Acta Polym.*, **46**, 87 (1995)
5. Ardoin N., Astruc D., Dendrimers Designed for Functions: From Physical, Photophysical and Supramolecular Properties to Applications in Sensing, Catalysis, Molecular Electronics, Photonics and Nanomedicine, *Bul. Soc. Chim. Fr.*, **132**, 875 (1995)
6. Zeng F., Zimmerman S.T., Synthesis of Cored Dendrimers, *Chem. Rev.*, **97**, 1681 (1997)

7. Johan F.G., Jansen A., Elien M.M., de Brabander- van den Berg, Meijer E.W., The Dendritic Box: Shape-Selective Liberation of 1) shell deprotection Encapsulated Guests, **266**, *Science*, 1226 (1994)
 8. Roberts J.C., Bhalbat M.K., Zera R.T., PEGylated Dendritic Architecture for Development of a Prolonged Drug Delivery System for an Antitubercular Drug. Res., *J. Biomedical. Mater*, **30**, 53 (1996)
 9. Malik N., Wiwattanapapee R., Klopsch R., Lorenz K., Frey H., Weener J.W., Meijer E.W. and Paulus W., Duncan R., Intracellular macrophage uptake of rifampicin loaded mannosylated dendrimers, *J. Control.Release*, **65**, 133 (2000)
 10. Neerman M.F., Chen H.T. and Parrish A.R., Simanek E.E., Reduction of drug toxicity using dendrimers based on melamine, *Mol.Pharm.*, 390 (2004)
 11. Chen H.T., Neerman M.F., Parrish A.R. and Simanek E.E., Cytotoxicity, hemolysis acute invivo toxicity of dendrimers basedon melamine, candidate vehicle for drug delivery, *J. Am.Chem. Soc.*, **126**, 10044 (2004)
 12. Bhadra D., Bhadra S., Jain P. and Jain N.K., Pegnology: a review of PEG-ylated systems *Pharmazie.*, **57**, 5 (2002)
 13. Bhadra D., Bhadra S. and Jain N.K, PEGylated peptide-based dendritic nanoparticulate systems for delivery of artemether, *J. Drug Del. Sci. Tech.*, **15**, 65 (2005)
 14. Abuchowski A., Palczuk N.C., Van Es T.and Davis F.F., Alteration of immunological properties of bovine serum albumin by covalent attachment of polyethylene glycol, *J. Biol. Chem.*, **252**, 3578 (1977)
 15. Abuchowski A., McCoy J.R., Palczuk N.C., van Es T. and Davis F.F., Effect of covalent attachment of polyethylene glycol on immunogenicity and circulating life of bovine liver catalase, *J. Bio. Chem.*, **252**, 3582 (1977)
 16. Yokoyama M., Okano T., Sakurai Y., Ekimoto H., Shibazaki C. and Kataoka K., *Cancer. Res.*, **51**, 3229 (1991)
 17. Klibanov A., Maruyama K., Torchilin V.P. and Huang L., Amphipathic polyethyleneglycols effectively prolong the circulation time of liposomes, *FEBS Lett.*, **268**, 235 (1990)
 18. Blume B. and Cevc G., Liposomes for the sustained drug release in vivo. *Biochim Biophys Acta.*, **2**, 1029(1), 91–97 (1990)
 19. Woodle M.C., Lasic D.D., *BioChim. Biophys. Acta.*, **1113**, 171 (1992)
 20. Lasic D.D. and Needham D., stealth liposomes: a prototypical biomaterial, *Chem. Rev.*, **95**, 2601 (1995)
 21. Margerum, L.D., Campion, B.K., Koo, M., Shargill, N., Lai, J.J., Marumoto, A. and Sontum, P.C., *J. Alloys Compd.*, **249**, 185-190 (1997)
- Norrel S.A. and Messley K.E., Microbiology Laboratory Manual Principles and Applications. Prentice Hall, Upper Saddle River, New Jersey (1997)

Table-1
Antibacterial Activity of Levofloxacin Loaded Dendrimers against Resistant Producing Microorganisms

@	Treatment	Klebsiella pneumonia	E.coli
1	Control(DMSO)	NZI	NZI
2	Standard (Levofloxacin (100mcg/ml))	NZI	NZI
3	DLD(50mcg/ml)	0.96±0.15	0.9±0.05
4	DLD(100mcg/ml)	1.0±0.05	1.0±0.23

NZI - No zone of inhibition; DLD - Drug loaded dendrimer; DMSO- Dimethyl sulphoxide



Figure-1
No zone of inhibition produced by pure levofloxacin against E. coli



Figure-2
No zone of inhibition produced by pure levofloxacin against K. Pneumonia



Figure-3
Control solvent DMSO was not produced zone against E. coli



Figure- 4
Control solvent DMSO was not produced zone against K. pneumonia



Figure-5
Zonal inhibition produced by 100 µg/ml of levofloxacin loaded Dendrimer against K. Pneumonia



Figure-6
Zonal inhibition produced by 100 µg/ml of levofloxacin loaded Dendrimer against E. coli