

Growth, structural and opto-electrical studies of glycine doped malic acid crystal for nonlinear applications

Mohd Anis

Crystal Growth Laboratory, Department of Physics, Milliya Arts Science and Management Science College, Beed-431122, Maharashtra, INDIA

Available online at: www.isca.in, www.isca.me

Received 29th October 2013, revised 9th January 2014, accepted 4th February 2014

Abstract

The present communication reports impact on structural, optical and dielectric properties of optically active glycine doped malic acid crystal. The grown crystal was subjected to powder XRD, UV-Vis studies, FT-IR analysis and SEM characterizations. The structure and surface morphology has been examined by powder XRD and SEM analysis. The UV-Vis studies revealed high transparency and cut off was found to be 361 nm imperative to evaluate the electronic band structure and optical properties. The grown crystal inherits wide band gap, low susceptibility and high optical conductivity eminent for optical device fabrication. The lower dielectric characteristics were ascertained from dielectric studies. The imprints of glycine were evaluated by FTIR analysis.

Keywords: XRD, UV-vis studies, dielectric studies, SEM analysis, FTIR analysis.

Introduction

In past decade more attention had been drawn by the organic NLO materials due to their vital physico-chemical properties essential for electro-optic modulation, laser applications, optical switching and data storage, phase matching and NLO applications. Organic materials possess high chirality, exceptionally wide bandwidth potential, excellent nonlinear activity than inorganic materials¹⁻³. Many researchers had attributed studies on improved structural, thermal, optical and electrical properties due to mixing equimolar ratios of L-alanine, L-arginine with malic acid, oxalic acid, nitric acid acetic acid cited in literature²⁻⁶. Amino acids possess proton donor carboxyl acid (-COO) group and the proton acceptor amino (NH₂) group. The amino acids glycine, arginine, l-alanine and lysine are evidently showing NLO activity due to donor-acceptor groups and also intermediate charge transfer was possible. Glycine (C₂H₅NO₂) is the simplest of all amino acid, has three polymeric crystalline forms: α , β and γ . The α and β forms crystallize in centrosymmetric while γ -glycine crystallizes in non-centrosymmetric space group⁷. As per the literature survey glycine had been doped in host materials KDP and thiourea complexes by Hussaini et.al⁸⁻⁹. In present investigation crystal of glycine doped malic acid crystal has been synthesized and characterized by powder XRD, UV-Vis and dielectric studies, FT-IR analysis and SEM analysis.

Methodology

The supersaturation of host material malic acid was attained in deionized water at room temperature. 1 mole% of optically active glycine had been mixed and was stirred well for six hours at a constant speed to achieve the homogeneity throughout the volume. The solution is then filtered and kept for evaporation at

room temperature. The purity was achieved by successive recrystallisation. The photograph shows good quality transparent crystals of glycine doped malic acid cited in figure 1.




Figure-1
Photograph of glycine doped malic acid

Results and Discussion

X-Ray Diffraction Analysis: The sample of the grown crystal was subjected to powder X-ray diffraction analysis using Panalytical, XPert PRO powder X-ray diffractometer employing CuK α radiation ($\lambda = 1.5418 \text{ \AA}$). The XRD pattern of glycine doped malic acid crystal, seen in figure 2. The observed peaks in the spectrum indicates the resemblance of grown

crystal to orthorhombic structure. The evaluated cell parameters are $a=7.255\text{\AA}$, $b=10.7\text{\AA}$, $c=8.746\text{\AA}$.

characteristic wavelengths of glycine. The absorption peaks within the range of 2000 to 3750 cm^{-1} contributes to the N-H and C-H stretching vibrations.




Figure-2
 XRD pattern of Glycine doped Malic Acid




Figure-4
 UV Transmittance Spectrum




Figure-3
 FT-IR Spectrum




Figure-5
 $(\alpha h\nu)^2$ vs. $h\nu$ in eV

FTIR Analysis: The incorporation of glycine in malic acid was evaluated by FTIR analysis. The absorption spectrum was recorded within the range of 600 to 4000 cm^{-1} by Bruker α -ATR visualized in figure 3. Glycine shows characteristic functional groups at 504 , 658 , 858 , 1410 , 1501 , 1613 , cm^{-1} . The absorption peaks at 639 and 747 cm^{-1} contributes to the $-\text{COO}^-$ plane deformation. The C-C stretching is observed at 854 cm^{-1} . The absorption peak at 1055 cm^{-1} is evident of C-C-N bond stretching. The NH_3^+ asymmetric stretching is observed at 1507 , 1608 , 1700 cm^{-1} which appears to be in good agreement with the

UV-Vis Studies: The transmittance spectrum shown in figure 4 was recorded using Shimadzu UV-2450 spectrophotometer within the range of 200 - 900 nm . The lower cutoff wavelength of 361 nm and high transmittance above 85% led least absorption in entire visible region affirms high optical transparency and wide transmittance range of the grown crystal imperative for NLO applications. The absorption coefficient is evaluated using the transmittance spectrum as

$$\alpha = \frac{2.303 \log\left[\frac{1}{T}\right]}{d} \quad (1)$$

Where T is the transmittance, α is the absorption coefficient, d is the thickness of the crystal Optical band gap (E_g) depicted in figure 3 was calculated by

$$\alpha = A(h\nu - E_g)^{\frac{1}{2}} \quad (2)$$

Extinction coefficient can be obtained by the following relation,

$$k = \frac{\alpha\lambda}{4\pi} \quad (3)$$

Reflectance in terms of refractive index (n) is given by relations respectively,

$$R = \frac{(n-1)^2}{(n+1)^2} \quad (4)$$

The variation of $(\alpha h\nu)^2$ versus $h\nu$ in the fundamental absorption region is plotted in figure 5 and E_g is evaluated by extrapolation of the linear part. The remarkably wide optical band gap of 3.66 eV highly imperative for optical device fabrication. The figure 6 & 8 display decrementing values of refractive index, extinction coefficient, reflectance with increasing wavelength essential optical parameters for antireflection coating in solar thermal devices and high optical conductivity (10^{10} s^{-1}) response depicted in figure-9 is requisite for device applications in information processing and computing¹¹. The ac susceptibility observed from figure-10 found to be greater than 1 which indicates material is more prone to polarize in intense light¹². The electrical susceptibility was calculated using the relation,

$$\chi_c = n^2 - 1 \quad (5)$$

The relation between band gap and refractive index is given as $E_g e^n = 18.12$ (6)




Figure-6
 Refractive Index vs. Wavelength




Figure-7
 Reflectance vs. Wavelength




Figure-8
 Extinction Coefficient vs. Wavelength

Dielectric Studies: The dielectric studies were carried at room temperature using Gwinstek LCR-819 meter within the range 10 Hz to 100 KHz. The variation of dielectric constant and dielectric loss are represented in figure-11 and 12 respectively. The higher values of dielectric constant at lower frequency are attributed due to four polarization mechanism. The lower values of dielectric constant at higher frequencies are due to low contribution of polarization mechanism. However grown crystal exhibited lower dielectric constant over entire frequency which is eminently needed for enhancement of SHG coefficient and optical quality of grown crystal¹². The lower dielectric loss at higher frequency confirmed the lower defects concentration and the low energy dissipation¹². The lower dielectric constant and

dielectric loss indicated the grown crystal is potential candidate for NLO applications¹².




Figure-9
 Optical Conductivity vs. hv in eV




Figure-11
 Dielectric Constant vs. Log F




Figure-10
 ac susceptibility vs. Wavelength




Figure-12
 Dielectric Loss vs. Log F

Table-1
 Optical constants

| Parameters | Malic Acid + Glycine 1Mole | Potassium Dihydrogen Phosphate [KDP] |
|------------------------|----------------------------|--------------------------------------|
| Refractive Index | 1.61 | 2.04 |
| Reflectance | 23 | 34.09 |
| Extinction coefficient | 2.41×10^{-5} | 9.6×10^{-5} |
| ac susceptibility | 1.59 | 3.16 |
| $E_g e^n$ | 18.12 | 36.14 |

Scan Electron Microscopy Analysis: The Scanning electron microscopy (SEM) image of the grown crystal was recorded using HITACHI S4800 to study the surface morphology of glycine doped malic acid crystal. The figure 13 depicts the layer formations on the surface of the grown crystal at a 100μm scale. It is evident that the grown crystal shows stepped growth which may be the consequence of constant rate of evaporation of solvent at room temperature.




Figure-13
SEM Photograph

Conclusion

The good quality transparent glycine doped malic acid crystal has been grown and structural and optical studies were performed. The employed powder XRD verified the orthorhombic structure of the grown crystal. FT-IR analysis confirmed the incorporation of different functional groups of glycine. The cut off wavelength was ascertained to be 361nm from UV spectrum. The attribution of glycine had employed to enhance optical parameters eminently better than KDP substantive for NLO applications. The band gap of grown crystal was found to be 3.66 eV highly demanded for optoelectronic device fabrications. The dielectric studies confirmed high optical quality and lower defects concentration in grown crystal. The SEM study revealed the stepped growth of the grown crystal.

References

1. Hussaini S.S., Dhumane N.R., Dongre V.G., Shirsat M.D., Growth and characterization of an NLO material – crystal of triglycine acetate, *Mater. Sci.*, **27(2)**, 365-372 (2009)
2. Martin Britto Dhas S.A., Bhagavannarayana G. and Natarajan S., Growth, HRXRD, Microhardness and Dielectric Studies on the NLO Material L-Alaninium Maleate, *The open crystallo. J.*, **1**, 42-45 (2008)
3. Karunanithi U., Arulmozhi S. and Madhavan J., Synthesis and Characterization of Pure and Doped L- Arginine Maleate Single Crystals, *J. Appl. Phys.*, **1(2)**, 14-18 (2012)
4. Mohan Kumara R., Rajan Babub D., Jayaramanc D., Jayaveld R. and Kitamura K., Studies on the growth aspects of semi-organic L-alanine acetate: a promising NLO crystal, *J. Cryst. Growth*, **275**, 1935-1939 (2005)
5. Arun K.J. and Jayalekshmi S., Growth and Characterisation of Nonlinear Optical Single Crystals of L-Alaninium Oxalate, *J. Minrl. Mater. Char. & Engr.*, **8(8)**, 635-646 (2009)
6. Praveen Kumar P., Manivannan V., Sagayaraj P. and Madhavan J., Growth and characterization of pure and doped NLO L-arginine acetate single crystals, *Bull. Mater. Sci.*, **32(4)**, 431-435 (2009)
7. Sekar C. and Parimaladevi R., Effect of silver nitrate (AgNO₃) on the growth, optical, spectral, thermal and mechanical properties of γ -glycine single crystal, *J. optoelectrnics. Biomdcl. Minerals*, **1(2)**, 215-225 (2009)
8. Hussaini S.S., Dhumane N.R., Dongre V.G., Shirsat M.D., Effect of Glycine on Optical and Thermal Properties of KDP Single Crystal, *Frnt. Micro. Optoelectrnics*, **19(6)**, 196-201 (2008)
9. Hussaini S.S., Dhumane N.R., Dongre V.G. and Shirsat M.D., Effect of glycine on the optical properties of Zinc Thiourea Chloride (ZTC) single crystal, *Optoelectrnics. Advc. Mater.*, **2(2)**, 108-112 (2008)
10. Kavitha P., Shanthi J., and Deepthi P. R., Optical Properties and Density Functional Theory Study of Single Crystal Glycine, *Intrl. J. App. Phys. Math.*, **2(4)**, 293-295 (2012)
11. Sabari Girisun T. C. and Dhanuskodi S., Linear and nonlinear optical properties of tris thiourea zinc sulphate single crystals, *Cryst. Res. Technol.*, **44(12)**, 1297-1302 (2009)
12. Vasudevan P., Sankar S. and Jayaraman D., Synthesis, Optical and Electrical Studies of Nonlinear Optical Crystal: L-Arginine Semi-oxalate, *Bull. Korean Chem. Soc.*, **34(1)**, 128-132 (2013)